IN THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Previously Presented): A precipitated silica characterized by

BET $350 - 550 \text{ m}^2/\text{g}$

DBP number 350 - 400 g/100 g

 d_{50} 5 - 15 μ m, and

tamped density 20 to less than 70 g/l.

2. (Original): The precipitated silica as claimed in claim 1, wherein the particle size distribution

$$\frac{d_{90} - d_{10}}{d_{50}}$$

is from 0.90 to 1.5.

3. (Original): The precipitated silica as claimed in claim 1, wherein the gloss angle gloss values are:

60° 15 - 25 and

85° 50 - 70.

4. (Original): The precipitated silica as claimed in claim 2, wherein the gloss angle gloss values are:

60° 15 - 25 and

Application No. 10/656,164 Amendment

85° 50 - 70.

- 5. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 1 as a matting agent to said paint or ink.
- 6. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 1 as a matting agent.
- 7. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 2 as a matting agent to said paint or ink.
- 8. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 2 as a matting agent.
- 9. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 3 as a matting agent to said paint or ink.
- 10. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 3 as a matting agent.
- 11. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 4 as a matting agent to said paint or ink.
- 12. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 4 as a matting agent.
 - 13. (Previously Presented): A wax-coated precipitated silica characterized by

Application No. 10/656,164 Amendment

BET
$$350 - 550 \text{ m}^2/\text{g}$$

$$d_{50}$$
 5 - 15 μm

14. (Original): The wax-coated precipitated silica as claimed in claim 13, wherein the particle size distribution

$$\frac{d_{90} - d_{10}}{d_{50}}$$

is from 0.90 to 1.5.

15. (Original): A wax-coated precipitated silica as claimed in claim 13, wherein the gloss angle gloss values are:

60° 15 - 25 and

85° 50 - 70.

16. (Original): A wax-coated precipitated silica as claimed in claim 14, wherein the gloss angle gloss values are:

60° 15 - 25 and

85° 50 - 70.

- 17. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 13 as a matting agent to said paint or ink.
- 18. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 13 as a matting agent.
- 19. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 14 as a matting agent to said paint or ink.
- 20. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 14 as a matting agent.
- 21. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 15 as a matting agent to said paint or ink.
- 22. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 15 as a matting agent.
- 23. (Currently Amended): A process for increasing the matting effect of a paint or ink comprising adding the precipitated silica as claimed in claim 16 as a matting agent to said paint or ink.

- 24. (Original): A paint or ink, which includes the precipitated silica as claimed in claim 16 as a matting agent.
- 25. (Previously Presented): The precipitated silica as claimed in claim 1, wherein the d_{50} value is from 7-11 μ m.
- 26. (Previously Presented): The wax-coated precipitated silica as claimed in claim 13, wherein the d_{50} value is from 7-11 μ m.
- 27. (Previously Presented): The precipitated silica as claimed in claim 1, wherein the tamped density is 20-60 g/l.
- 28. (Previously Presented): The wax-coated precipitated silica as claimed in claim 13, wherein the tamped density is 20-60 g/l.